

Physical Inspection Sheet

Inspected By ALM
Sample ID 1-0-1935-36

Date of Inspection 1/30/13
RTI Yes or No

DMin : .86

DMax 2.05

DSprocket .17

Thickness .062

Condition Level:

0 = none

1 = Light (less than 1/3rd of frame affected)

2 = Moderate (1/3rd - 2/3rd frame affected)

3 = Heavy (more than 2/3rd frame affected)

1 scratch = .05 mm

Base Condition

Scratch Count:

Vertical .40

Horizontal 0

Brittleness: 0

Softness: 0

Yellowing: 0

Image Condition

Scratch Count:

Vertical 0

Horizontal .05

Stickiness: 0

Faded/Bleached: 0

Amount of Image Gone (in mm): 0

Physical Damage

Buckle 1

of Sprockets Broken 0

Tears 0

Folds 0

Foreign Matter

Dirt 0

Grease/Oil 0

Brown Powder 0

Adhesive residue 0

Notes:

Physical Inspection Sheet

Inspected By ALM
Sample ID 2-2-1919-25

Date of Inspection 2/4/13
RTI Yes or No

DMin .14 DMax .94 DSprocket .17
Thickness .057

Condition Level:

- 0 = none
- 1 = Light (less than 1/3rd of frame affected)
- 2 = Moderate (1/3rd - 2/3rd frame affected)
- 3 = Heavy (more than 2/3rd frame affected)

1 scratch = .05 mm

Base Condition

Scratch Count: Vertical 18m Horizontal .05m
Brittleness: 1 Softness: 0
Yellowing: 0 Yes or No

Image Condition

Scratch Count: Vertical 20m Horizontal 0m
Stickiness: 0 Faded/Bleached: 0
Amount of Image Gone (in mm): 0m

Physical Damage

Buckle 0 # of Sprockets Broken 0 Tears 0 Folds 0

Foreign Matter

Dirt 2 Grease/Oil 0 Brown Powder 0 Adhesive residue 0

Notes:

Physical Inspection Sheet

Inspected By ALM
Sample ID 3-4-1919-50

Date of Inspection 2/6/13
RTI Yes or No Yes

DMin .12 DMax .92

DSprocket .09

Thickness .063

Condition Level:

- 0 = none
- 1 = Light (less than 1/3rd of frame affected)
- 2 = Moderate (1/3rd - 2/3rd frame affected)
- 3 = Heavy (more than 2/3rd frame affected)

1 scratch = .05 mm

Base Condition

Scratch Count: Vertical 23m Horizontal 0m

Brittleness: 1 Softness: 0

Yellowing: Yes or No

Image Condition

Scratch Count: Vertical 10.6m Horizontal .15m

Stickiness: 1 Faded/Bleached: 2

Amount of Image Gone (in mm): 3m x 17m

Physical Damage

Buckle 0 # of Sprockets Broken 0 Tears 0 Folds 0

Foreign Matter

Dirt 1 Grease/Oil 0 Brown Powder 1 Adhesive residue 0

Notes:

Brown powder in can - residue may be dirt +/or bp.